


Claims

1. A phthalocyanine colorant represented by Formula (1):




5

[in Formula (1), M represents a hydrogen atom, a metal atom, a metal oxide, a metal hydroxide, or a metal halide; R₂, R₃, R₆, R₇, R₁₀, R₁₁, R₁₄ and R₁₅ each independently represent an unsubstituted sulfamoyl group represented by Formula (2), a substituted sulfamoyl group represented by Formula (3), or a hydrogen atom, provided that


10 at least one of R₂, R₃, R₆, R₇, R₁₀, R₁₁, R₁₄ and R₁₅ is an unsubstituted sulfamoyl group, and at least one thereof is a substituted sulfamoyl group represented by Formula (3); and R₁, R₄, R₅, R₈, R₉, R₁₂, R₁₃ and R₁₆ represent hydrogen atoms; the sum of a number of an

15 unsubstituted sulfamoyl group and a total number of a substituted sulfamoyl group is 2 to 4, and a number of an unsubstituted sulfamoyl group is 1 to 3 and a number of a substituted sulfamoyl group is 1 to 3.]:



5 ,in Formula (3), R_{17} and R_{18} each independently represent a hydrogen atom, a substituted or unsubstituted alkyl group, a substituted or unsubstituted cycloalkyl group, a substituted or unsubstituted aralkyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted heterocyclic group, and a substituted or unsubstituted alkenyl group; R_{17} and R_{18} may form a ring by bonding
10 together except when both R_{17} and R_{18} represent a halogen atom; and at least one of R_{17} and R_{18} has an ionic and hydrophilic group as a substituent.

2. The phthalocyanine colorant according to Claim 1, wherein Formula (1) according to Claim 1 wherein M is Cu, is represented
15 by Formula (4):



, in Formula (4), R_1 to R_{16} mean the same as in Formula (1).

3. The phthalocyanine colorant according to Claim 1 or Claim 2, wherein in each of combinations of R_2 and R_3 , R_6 and R_7 , R_{10} and R_{11} , and R_{14} and R_{15} , one member of each combination is a hydrogen atom, and the other is an unsubstituted sulfamoyl group represented by Formula (2), a substituted sulfamoyl group represented by Formula (3) or a hydrogen atom, and among R_2 , R_3 , R_6 , R_7 , R_{10} , R_{11} , R_{14} and R_{15} , at least one is an unsubstituted sulfamoyl group and at least one is a substituted sulfamoyl group represented by Formula (3).

4. The phthalocyanine colorant according to any one of Claims 1 to 3, wherein R_{17} and R_{18} each independently represent a hydrogen atom, an alkyl group (which may be substituted with a substituent selected from a group consisting of a sulfonic acid group, a carboxyl group, a hydroxyl group, an alkoxy group, a dialkylamino group, an arylamino group, an aryl group, a halogen atom and a cyano group), a phenyl group (which may be substituted with one or more substituents selected from a group consisting of a sulfonic acid group, a carboxyl group, a hydroxyl group, a dialkylamino group, an arylamino group, an acetylamino group, a ureido group, an alkyl group, an alkoxy group, a nitro group, a cyano group, a heterocyclic group and a halogen atom), a naphthyl group (which may be substituted with a sulfonic acid group or a hydroxyl group), a benzyl group (which may be substituted with a sulfonic acid group) and a phenethyl group (which may be substituted with a sulfonic acid group).

5. The phthalocyanine colorant according to any one of Claims 1 to 3, wherein R_{17} is a hydrogen atom, a carboxyl(C1 to C5)alkyl

group, a (C1 to C5)alkyl group, a hydroxyl(C1 to C5)alkyl group and a sulfo(C1 to C5)alkyl group; and R₁₈ is a phenyl group having a sulfo(C1 to C5)alkyl group, a carboxyl(C1 to C5)alkyl group, a sulfonic acid group, a carboxyl group or a hydroxyl group, a

5 benzotriazolyl group substituted with a phenyl group having a di(sulfo(C1 to C5)alkyl) amino(C1 to C5)alkyl group, a sulfonic acid group, a carboxyl group or a hydroxyl group, a phenyl group substituted with a benzotriazol group having a sulfonic acid group, a carboxyl group or a hydroxyl group, a naphthyl group having a

10 sulfonic acid group or a hydroxyl group, a uracil group having a sulfonic acid group, a carboxyl group or a hydroxyl group, a triazol group having a sulfonic acid group, a carboxyl group or a hydroxyl group, a thiazolyl group having a sulfonic acid group, a carboxyl group or a hydroxyl group, a benzothiazolyl group having a sulfonic


15 acid group, a carboxyl group or a hydroxyl group, a pyridine group having a sulfonic acid group, a carboxyl group or a hydroxyl group, and a benzimidazolyl group having a sulfonic acid group, a carboxyl group or a hydroxyl group.

6. The phthalocyanine colorant according to Claim 1, wherein

20 content of the colorant represented by Formula (1) is at least not less than 60% based on total colorants.

7. The phthalocyanine colorant according to any one of Claims 1 to 5, wherein the colorant represented by Formula (1) is obtained by subjecting the phthalocyanine colorant represented by Formula

25 (5):



(in Formula (5), respectively, M represents a hydrogen atom, a metal atom, a metal oxide or a metal halide; L represents a proton, an alkaline metal ion, an alkaline earth metal ion and an onium ion of an organic amine or ammonium ion; and a, b, c and d are 0 or 1, provided that the sum thereof is an integer of 2 to 4) or a salt thereof to reaction with a chlorinating reagent to convert a sulfonic acid group to a chlorosulfonyl group and subsequent reaction with an amidating reagent in the presence of an organic amine.

8. A phthalocyanine colorant obtained by subjecting 4-sulfophthalic acid derivatives themselves to reaction with a metallo compound in the presence of the metallo compound, followed by subjecting thus obtained sulfometallophthalocyanine compound or a salt thereof to reaction with a chlorinating reagent to convert a sulfonic acid group to a chlorosulfonyl group and subsequent reaction with an amidating reagent and an organic amine.

9. An ink characterized by comprising the phthalocyanine colorant according to any one of Claims 1 to 8, as a colorant component.

10. The ink according to Claim 9, wherein an organic solvent

is contained.

11. The ink according to Claim 9 or claim 10, which is used for ink-jet recording.

12. An ink set characterized, in an ink-jet printer using
5 not less than 2 kinds of cyan inks with different colorant density, by using, as at least one kind therefore, the ink according to any one of Claim 9 or 11.

13. An ink-jet recording method characterized by using the ink according to any one of Claims 9 to 11 or the ink set according
10 to Claim 12, in an ink-jet recording method wherein the recording is carried out onto a recording material by discharging ink droplets in response to recording signals.

14. The ink-jet recording method according to Claim 13 wherein the recording material is an information transmission
15 sheet.

15. Then ink-jet recording method according to Claim 14 wherein the information transmission sheet is a surface treated sheet having an ink image receiving layer containing white inorganic pigment particles on a carrier.

20 16. A container containing the ink or the ink set according to any one of Claims 9 to 12.


17. An ink-jet printer having the container according to Claim 16.

25 18. A colored product colored with the ink or the ink set according to any one of Claims 9 to 12.

19. A method for production of a phthalocyanie colorant characterized by subjecting 4-sulfophthalic acid derivatives to reaction with themselves or subjecting a 4-sulfophthalic acid derivative to reaction with a phthalic acid (phthalic anhydride)

derivative in the presence of a copper compound, followed by
 subjecting thus obtained compound or a salt thereof to reaction
 with a chlorinating reagent to convert a sulfonic acid group to
 a chlorosulfonyl group and subsequent reaction with an amidating
 5 reagent and an organic amine.

20. A phthalocyanine colorant wherein, in the phthalocyanine
 colorant represented by the following general Formula (9):




10

(wherein M represents a hydrogen atom, a metal atom, a metal oxide,
 a metal hydroxide or a metal halide; l includes 0 and smaller than
 1; m is not smaller than 1 and not larger than 3.7; n is not smaller
 than 0.3 and not larger than 3; sum of l, m and n is not smaller
 15 than 2 and not larger than 4; R₁₇ and R₁₈ each independently represent
 a hydrogen atom, a substituted or unsubstituted alkyl group, a
 substituted or unsubstituted cycloalkyl group, a substituted or
 unsubstituted aralkyl group, a substituted or unsubstituted aryl
 group, a substituted or unsubstituted heterocyclic group, and a
 20 substituted or unsubstituted alkenyl group; R₁₇ and R₁₈ may form
 a ring by bonding together, provided that except when both R₁₇ and
 R₁₈ represent a hydrogen atom; and at least one of R₁₇ and R₁₈ has
 an ionic and hydrophilic group as a substituent.),

a β -substituted compound is not less than 60% and an α -substituted compound is not more than 40%.

21. A mixture of colorants represented by the following general Formula (10):



{wherein R_2' , R_3' , R_6' , R_7' , R_{10}' , R_{11}' , R_{14}' and R_{15}' each independently represent an unsubstituted sulfamoyl group ($-\text{SO}_2\text{NH}_2$), a sulfone group ($-\text{SO}_3\text{M}'$) or a hydrogen atom, provided that at least one of R_2' , R_3' , R_6' , R_7' , R_{10}' , R_{11}' , R_{14}' and R_{15}' is an unsubstituted sulfamoyl group; R_1 , R_4 , R_5 , R_8 , R_9 , R_{12} , R_{13} and R_{16} represent hydrogen atoms; and M' represents a proton, an alkaline metal ion, an alkaline earth metal ion and an onium ion of an organic amine or ammonium ion.}

22. A mixture of colorants obtained by subjecting 4-sulfophthalic acid derivatives, or a 4-sulfophthalic acid derivative and a phthalic acid (phthalic anhydride) derivative to reaction with a copper compound in the presence of a copper compound, followed by subjecting thus obtained compound or a salt thereof to reaction with a chlorinating reagent to convert a sulfonic acid group to a chlorosulfonyl group and subsequent reaction with an amidating reagent.

Abstract

The present invention relates to a phthalocyanine colorant characterized in that it has, as substituents, at least one unsubstituted sulfamoyl group and at least one substituted
5 sulfamoyl group, the total number of these groups being 2 to 4, and the unsubstituted sulfamoyl group and the substituted sulfamoyl group are bonded to the phthalocyanine ring at the 8-position. Said phthalocyanine colorant is suitable for use in an ink, especially a cyan ink, for an ink-jet printer. A printed matter obtained by
10 printing with said ink is excellent in light fastness, ozone fastness and moisture fastness.